Derwent Record

View: Expand Details Go to: Delphion Integrated View

Aerated cement granules prodn. - by comminuting aerated cement before Propert Title:

hardening

Original Title: DE3213521A1: Verfahren zur Herstellung von poroesen Granulaten fuer

industrielle Zwecke sowie Verwendung solcher Granulate

YXHULT AB Non-standard company **P**Assignee:

YTONG AG Standard company

Other publications from YTONG AG (YTON)...

LARSSON I: **V**Inventor:

1983-61521K / 198326

Update:

A62C 1/24; A62D 1/00; A62D 3/00; B01J 2/00; C02F 1/40; PIPC Code:

C04B 14/02; C04B 15/02; C04B 21/00; C04B 28/02; C04B 28/18; C04B 31/02; C04B 38/00; C09K 3/32; E02B 15/04;

E04F 13/02;

Prwent Classes: D15; H03; K01; L02; P35; Q42; Q45;

@ Manual Codes: D04-B03(Removal of mineral oil, hydrocarbons, coal slurry),

H03-G(General), K01-A(General), L02-D03(Light concretes)

(DE3213521A) Prodn. of porous granules from a mixt. of a CaO-contg. binder (e.g. lime or Portland cement) and a SiO2-contg. material (e.g. quartz sand, spent shale Abstract:

or fly ash) is carried out by (a) slurrying the mixt, with water and a blowing agent; (b) pouring the slurry into a mould and allowing it to set into a porous, self-supporting, semi-plastic material; (c) comminuting the material to obtain granules; and (d)

hardening the granules, e.g. by steaming.

The granules can be used as absorbents (e.g. for cleaning up oil spills), for extinguishing fires, as ballast material or as fillers (e.g. in plastering compsns.)

PFamily: PDF Patent Pub. Date Derwent Update Pages Language IPC Code

A62D 1/00 DE3213521A * 1983-06-23 198326 14 German

Local appls.: <u>DE1982003213521</u> Filed:1982-04-10 (82DE-3213521)

AT8201439A = 1988-11-15 198851

Local appls.:

☑ DE3213521C = 1987-08-13 198732 German A62D 1/00

Local appls.:

CH0649227A = 1985-05-15 198526 German A62C 1/24

Local appls.:

SE8107536A = 1983-07-18 198331 SV SV C04B 21/00

Local appls.:

BEST AVAILABLE COPY

§INPADOC Legal Status:

Show legal status actions

Show all claims 1. Verfahren zur Herstellung von poroesen, fuer industrielle Zwecke einsetzbaren Granulaten aus einer Ausgangsmischung, bestehend aus mindestens einem kalkhaltigen Bindemittel (z.B. Kalk, Portlandzement), mindestens einem kieselsaeurehaltigen Material (z.B. Quarzsand, Schieferasche, Flugasche u.s.w.) sowie Wasser, die in fluessigem Zustand zu einer Masse gegossen wird, und der dabei Makroporen verliehen werden, z.B. indem man der Ausgangsmischung gas- oder schaumbildende Mittel hinzufuegt, wobei der derart gegossenen Masse nach Bildung der Poren und dem Abbinden zu einer selbsttragenden, halbplastischen Konsistent ueberwiegend eine kristalline Struktur durch Haerten, z.B. durch Dampfhaerten, verliehen wird, dadurch gekennzeichnet, dass die

halbplastischen Konsistent ueberwiegend eine kristalline Struktur durch Haerten, z.B. durch Dampfhaerten, verliehen wird, dadurch gekennzeichnet, dass die gegossene Masse nach dem Abbinden, aber vor dem Haerten, wenn die Masse noch halbplastisch ist, zu Granulaten zerkleinert wird, die wiederum in diesem Zustand dem genannten Haerten ausgesetzt und danach fuer betreffende

industrielle Zwecke eingesetzt werden.

Priority Number:

Application Number	Filed	Original Title
SE1981000007536	1981-12-16	

AERATE CEMENT GRANULE PRODUCE COMMINUTE AERATE CEMENT

HARDEN

Pricing Current charges

Derwent Searches: Boolean | Accession/Number | Advanced

Data copyright Thomson Derwent 2003

© 1997-2004 Thomson

Research Subscriptions | Privacy Policy | Terms & Conditions | Site Map | Contact Us | H